



Technical Data Sheet

KEY101 Key Mask Liquid Spray Masking

Key Mask is a fast drying liquid spray masking material. Key Mask prevents primer, paint and various oversprays from adhering to painted surfaces. Key Mask dries to a tack free film in only 20-30 minutes and requires no special equipment to apply. Key Mask is easily and thoroughly rinsed off with water upon completion.

Directions:

1. Apply one wet coat with a conventional, gravity or HVLP spray gun using a 1.8 – 2.0 fluid nozzle.
2. Use 35 – 45 psi with gravity gun, 40 – 50 for siphon gun and 10 – 15 psi with HVLP equipment.
3. After completing the priming, painting and buffing processes, simply wet vehicle, allowing water to stand for 2 – 3 minutes before thoroughly rinsing.
4. Key Mask can be baked at 170° F without losing its masking properties.
5. One coat of Key Mask should dry in approximately 20 – 30 minutes at 70° F.

Caution:

1. Avoid contact with skin.
2. Use protective equipment when spraying.